

MOLYDUVAL

Ciric CHM 20 K



High Temperature Metal-Compound

A very soft special paste for lubrication of bolt connections and sliding surfaces at highest temperatures. Burning, seizing and rusting is prevented even under difficult conditions. A high portion of solid lubricants, predominantly metallic powders as copper, provides connections from seizure and increases separation efficiency.

Properties

- * good anticorrosive properties
- * exceptional lubricating and separating properties
- * prevents seizure and rust
- * good sealing properties against corrosive gases and fluids
- * free of sulfure
- * free of lead and nickel
- * resistant to water
- * suitable for centralized lubrication systems
- * good heat deduction
- * low friction coefficient
- * very soft

Applications

- * for preparation of packings
- * for hot screw connections at turbines, exhausts, cogwheels, valves, chains, slidings, waves
- * for wheel bearings of trolleys in drying chambers, for example in brickyards, pottery and porcelain factories
- * for slidings, guidelines, joints at slow moves and high pressures
- * for tool and workpiece lubrication in hot metal forming like forging or moulding
- * for bolts on brake systems, brake cams and back supports
- * for bearings at calenders
- * as release agent in high temperature range
- * for pump seals in case of chlorine, gasoline, or other corrosive liquids
- * for brake pad back sides at disk brakes
- * for hot screws, nuts, locks, at extreme high temperatures
- * for sliding surfaces in foundries, steel plants, galls production

Technical Datas

Color		copper
Consistency Class NLGI		ca. 00
Name		MPF00U-20
Base Fluid		Min
Name		ISO-L-XBGEB00
Density 15°C	kg/m ³	1000
Viscosity Base Fluid, 40°C	mm ² /s	220
Water Resistance Static	Grade	0
Temperature Range	°C	-20 -> +1200
Flash Point Base Fluid	°C	240

The indicated service temperatures are guide values depending on the lubricants composition and on the application. They may vary in case of special influences or ongoing use.

For further information, please see our website www.molyduval.com or consult your local representative.

The content of this manual is based on our current knowledge and experience in the development and manufacture of lubricants. Because of the complexity of tribological systems, the effect of our products depends on many parameters, which we cannot assess and which influence we cannot evaluate. For this reason general statements about the function of our products are not possible. The information in this manual, therefore, contains non-binding guidelines, which should give the technical trained reader information on possible applications. The information in this manual does not include property assurances or warranties or guarantees to the properties or suitability of this product in a specific application. Prior to its use it is absolutely necessary to test this product in the application to ensure that the product and its use is safe, economical and fully suitable. It should proceed with due diligence.